


ASTM D4541 TESTING
FOR SUPERIOR PRODUCTS
INTERNATIONAL II INC.
ON RUST GRIP
VTEC #100-2311
TESTED: DECEMBER 30, 2005



VTEC Laboratories Inc.

January 3, 2006

Client: Superior Products International II Inc.
10835 W. 78th St.
Shawnee, KS 66214

Attention: Mr. J.E. Pritchett

Scope: This report contains the reference to the test method, material description, test results, and post test observations/conclusions.

Test Method: This test was conducted in accordance with ASTM D4541, "Standard Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers"

Disclaimer: This is a factual report of the results obtained from the laboratory test of sample products. The results may be applied only to the products tested and should not be construed as applicable to other similar products of the manufacturer. The report is not a recommendation or disapprobation by VTEC Laboratories, Inc. of the material tested. While this report may be used for obtaining product acceptance, it may not be used in advertising.


Notice: VTEC Laboratories Inc. will not be liable for any loss or damage resulting from the use of the data in this report, in excess of the invoice. This report pertains to the sample tested only. Such report shall not be interpreted to be a warranty, either expressed or implied as to the suitability or fitness of said sample for such uses or applications, as the party contracting for the report may apply such sample.


Material:

1) Manufacturer:	Superior Products International II Inc.
2) Product Description:	Rust Grip
3) Coating Thickness:	6 mils
4) Color:	Gray
5) Surface:	Smooth
6) Substrate:	Steel
7) Substrate Dimensions:	12" x 12" x 3/8"
8) Dolly Diameter:	20 mm
9) Test Apparatus:	DeFelsko PosiTest Pull-Off Adhesion Tester
10) Adhesive:	Huntsman 2011 Araldite
11) Temperature:	66°F
12) Humidity:	46%

Test Results:

Dolly #	Failure Stress (psi)	Scoring Yes/No
1	1264	Yes
2	1536	Yes
3	1554	Yes
4	1353	Yes
5	1466	Yes
6	1593	Yes
7	1462	Yes
8	1578	Yes
9	1490	Yes
10	1372	Yes
Average	1467	


 Neil Schultz
 Executive Director.


 Amirudin Rahim
 Technical Director