# **RUST GRIP**

Rust Grip® is a metallic-based, moisture-cured polyurethane encapsulating coating that will coat over most surfaces to seal them up against further corrosion, weathering, and physical wear. Rust Grip® is a three-coats-in-one system that acts as a primer, intermediate, and topcoat in one.



# DESCRIPTION

Rust Grip® is a tough, one-part polyurethane coating that absorbs atmospheric moisture to cure. Rust Grip® is loaded with a metallic pigment for strength and is also resistant to chemical solvents and acid splash. Upon curing, Rust Grip® provides a protective coating film of superior adhesion and flexibility, and is resistant to abrasion and impact. Rust Grip® can be used as a primer or as a one-coating system. It is patented to encapsulate lead-based paints and other toxic materials, including asbestos. Rust Grip® can be applied over pressure-washed, dry flash rust and firmly bonded commercial paints. In most cases, a white or near-white blasting is not required.

# **BENEFITS**

- · Excellent for minimally prepared surfaces, ie. No sandblasting is required.
- Protects steel, aluminum, concrete, wood, fiberglass, lead-based paints, polyurethane foam, and other coatings.
- · Extremely tough, it makes an excellent floor coating.
- Submergible in 100% nitric acid without any effects. Designed to withstand acids, salts and caustics with no loss of strength.
- Rated as a Class A fire coating. In case of fire, Rust Grip® will help to prevent spread of, and will not contribute to, the burn.
- · Certified by the EPA for encapsulation of lead-based paints and asbestos.
- · Prevents mold and mildew from forming.
- · USDA approved for use in and around food preparation areas.
- · 15+ year lifespan on roofing under normal conditions.

### USES

- Corrosion and weathering protection. Rust Grip® is UV-controlled and is not affected by hostile environments.
- Overcoat rusted areas to stop and control corrosion activities. Rust Grip® will seal out any
  contact with moisture and air or chemical pollutants that breed corrosion activity.
- · Prime metal before over-coating.
- · Prevention of corrosion.
- · Protect floors to prevent wear and damage.
- · Anti-slip coating when combined with aggregates, for use around high traffic areas.
- Protection from acid splash or pooling. It will not allow acids to penetrate to affect the surface.
- Encapsulate and seal lead-based paints, asbestos, or other hazardous materials.





SC2 Trading

# **APPLICATION**

Rust Grip® can be applied to concrete or masonry substrates. The coating can be applied by spray, brush or roller. For specific instructions on surface preparation, mixing and application always follow the official application instructions.

### PHYSICAL DATA

- Solids: By weight 62.2% / By volume 51.4%
- 30-60 MINUTES TO TACK FREE AT 70°F (21°C)
- Overcoat window is three hours or less at 70°F (21°C)
- · Lead and chromate free
- Hygroscopic: Cures by absorbing moisture in the air
- · Weight: 9.8 lbs. per gallon
- · Moisture-cure Polyurethane
- Shelf Life: Up to 3 years (unopened) under appropriate storage condition (see MSDS)

### TESTS AND CERTIFICATIONS

- 1. Tensile Strength (6,780 psi after 3 weeks)
- 2. USDA approved
- 3. Marine approvals for salt water/maritime user:
  - · DNV (Det Norske Veritas)
  - · ABS (American Bureau of Shipping)
  - IMO (International Maritime Organization)
  - · US Coast Guard
- 4. Factory Mutual approval
- 5. E-108-00: Spread of flame on pitched roofs, Class "A"

- · One component coating; No curing agent needed
- · VOC Level: 400 grams/liter
- · Silver-gray in color; not available in colors
- · Resistant to most solvents, chemicals and some acids
- Maximum Surface Temperature when applying; 150°F (65°C)
- Minimum Surface Temperature when applying; 50°F (10°C)
- Maximum Surface Temperature after curing; 325°F (163°C)
- Failure will occur at a constant temperature equal to or greater than 325°F (163°C); consult SPI for intermittent temperatures greater than 325°F (163°C)
- 6. G85: Prohesion over rusted metal
- 7. Mildew Resistance excellent (ASTM D3273, 3274)
- 8. Chemical Resistance (24 hours/12 reagents)
- 9. Flexibility (Mandrel Bend: ASTM D522) 1/8"
- 10. Direct Impact Resistance (ASTM D2794)
- 11. Adhesion (ASTM D3359, D4541)
- 12. Water Vapor Transmission (ASTM D1653)
- 13. Surface Burning Characteristics (E84)
- 14. Weathering (2000 hours ) China
- 15. Scrub Resistance (ASTM D2486)

# Ship Deck - United States [before] Ship Deck - United States [after]

